

REMARKS

Claims 1- 26 are pending.


This Preliminary Amendment makes editorial revisions to the specification.

An Information Disclosure Statement and PTO-1449 directed to the art of record in the parent case are submitted herewith.

Early and favorable consideration of this application are respectfully requested.

Respectfully submitted,

Date: Aug 31, 2008

By:   
Anthony P. Venturino  
Registration No. 31,674

APV

ATTORNEY DOCKET NO. APV 31511

STEVENS, DAVIS, MILLER & MOSHER, L.L.P.  
1615 L STREET, N.W., SUITE 850  
WASHINGTON, D.C. 20036  
TEL. 202-785-0100 / FAX. 202-408-5200

## ATTACHMENT I - Marked up Claims

1. (Amended) Process for the wall ironing of a product in sheet form, which is formed from a metal sheet coated on at least one side with a layer of plastic, comprising  
moving the product with a plastic coating layer in a direction of movement along a forming surface of a [the] wall-ironing tool [comprising a forming surface which the product with a plastic coating layer moves along] during the wall ironing, [and] the forming surface being at an entry angle with respect to the direction of movement of the product, [characterized in that]

wherein the entry angle varies over the length of the forming surface, in the direction of movement of the product past the forming surface, this entry angle being smaller in a starting zone of the forming surface than in the subsequent zone thereof.

2. (Amended) Process according to Claim 1, [characterized in that] wherein the forming surface in an end zone is again at a smaller entry angle than in the intermediate zone.

3. (Amended) Process according to Claim 1 [or 2], [characterized in that] wherein the forming surface, following the zone with the largest entry angle, comprises a so-called land zone, with an entry angle = 0°.

4. (Amended) Process according to Claim 2 [or 3], [characterized in that] wherein the entry angle has a fixed value in each of the zones.

5. (Amended) Process according to Claim 2 [or 3], [characterized in that] wherein there is a smooth change in the entry angle over the length of the forming surface.

6. (Amended) Process according to Claim 5, [characterized in that] wherein the transitions between successive zones, and/or such zones themselves run in the form of an arc of a circle.

7. (Amended) Process according to [one of the preceding claims] Claim 1, [characterized in that] wherein the wall-ironing tool comprises a plurality of forming surfaces.

8. (Amended) Process according to Claim 1 [one of the preceding claims], [characterized in that] wherein the wall-ironing tool comprises a plurality of wall-ironing rings.

9. (Amended) Process according to Claim 1 [one of the preceding claims], [characterized in that] wherein 60 to 90% of the total wall thinning is produced by the corresponding forming surface in the zone running at the largest entry angle, the so-called main zone.

10. (Amended) Process according to Claim 9, [characterized in that] wherein 10 to 30% of the total wall thinning is produced by the corresponding forming surface in the starting zone.

11. (Amended) Process according to Claim 9 [or 10], [characterized in that] wherein less than 30% of the total wall thinning is produced by the corresponding forming surface in the end zone.

12. (Amended) Process according to Claim 1 [one of the preceding claims], [characterized in that] wherein the length of the starting zone and/or of the end zone, under otherwise identical conditions, is set in such a way that the plastic coating is not torn off the metal sheet as a result of the wall ironing.

13. (Amended) Process for the wall ironing of a product in sheet form, which is formed from a metal sheet coated on at least one side with a layer of plastic, comprising

moving the product with a plastic coating layer in a direction of movement along a forming surface of a [the] wall-ironing tool [comprising a forming surface which the product with a plastic coating layer moves along] during the wall ironing, [and] the forming surface being at an entry angle with respect to the direction of movement of the product, [characterized in that,]

wherein in a zone of the forming surface which runs at the largest entry angle, the plastic layer is held under an elevated pressure  $P_0$  (in MPa) on all sides, and [that] the plastic used for the coating layer is characterized by values of the parameters  $\mu$  (no units);  $\tau_0$  (in MPa) and  $A_0$  (in sec), [as defined in the description,] which are as follows:

$\mu \geq 0.03$  ;  $\tau_0 \geq 0.60$  and  $A_0 \geq 2.0 \times 10^{19}$ .

14. (Amended) Process according to Claim 13, [characterized in that] wherein the parameters  $\mu$ ,  $\tau_0$  and  $A_0$  are as follows:  $\mu \geq 0.047$ ;  $\tau_0 \geq 0.90$  and  $A_0 \geq 3.0 \times 10^{19}$ .

15. (Amended) Process according to Claim 13 [or 14], [characterized in that] wherein the plastic used is also characterized by values for the parameters  $T_{g, 1 \text{ atm}}$  and  $T_{g, 600 \text{ MPa}}$  (in °C) [, as defined in the description,] which are as follows:  $T_{g, 1 \text{ atm}} \geq 30^\circ\text{C}$ , and  $T_{g, 600 \text{ MPa}} \geq 200^\circ\text{C}$ .

16. (Amended) Process according to Claim 15, [characterized in that] wherein the parameter  $T_{g, 1 \text{ atm}}$  is as follows:  $T_{g, 1 \text{ atm}} \geq 70^\circ\text{C}$ .

17. (Amended) Wall-ironing tool[, in particular] comprising a wall-ironing ring, comprising a forming surface, along which a sheet-like product can be moved in a direction of movement during the wall ironing, which forming surface is at an entry angle with respect to the direction of movement of the product, [characterized in that] wherein the entry angle varies over the length of the forming surface, in the direction of movement of the product, this angle being smaller in a starting zone of the forming surface than in the subsequent zone thereof.

18. (Amended) Wall-ironing tool according to Claim 17, [characterized in that] wherein the subsequent zone is an intermediate zone and the forming surface further comprises [in] an end zone subsequent to the intermediate zone which is again at a smaller entry angle than in the intermediate zone.

19. (Amended) Wall-ironing tool according to Claim 17 [or 18], [characterized in that] wherein the forming surface further comprises an end zone, subsequent to the intermediate zone, and between the intermediate zone and the end zone there is a land zone with a length of between 0.3 and 1.5 mm.

20. (Amended) Wall-ironing tool according to one of [Claims 17-19] Claim 17, [characterized in that] wherein the entry angle has a fixed value in each of the zones.

21. (Amended) (Amended) Wall-ironing tool according to [one of Claims 17-19] Claim 17, [characterized in that] wherein there is a smooth change in the entry angle over the length of the forming surface.

22. (Amended) Wall-ironing tool according to Claim 21, [characterized in that] wherein the transitions between successive zone, and/or the zones themselves, run in the form of an arc of a circle with a radius of a length of between 0.1 and 10 mm.

23. (Amended) Wall-ironing tool according to [one of Claims 17-22] Claim 17, [characterized in that] wherein the [main] zone having the largest entry angle, which is named a main zone, forms between 60 and 90% of the transverse dimension of the forming surface, transversely with respect to its longitudinal direction.

24. (Amended) Wall-ironing tool according to Claim 23, [characterized in that] wherein the starting zone forms between 10 and 30% of the transverse dimension of the forming surface.

25. (Amended) Wall-ironing tool according to Claim 23 [or 24], [characterized in that] further comprising an end zone, subsequent to the intermediate zone, wherein the end zone forms less than 30% of the transverse dimension of the forming surface.

26. (Amended) Wall-ironing tool in the form of a wall-ironing ring, according to [one of Claims 17-25] Claim 17, [characterized in that] wherein this wall-ironing ring is under a radial prestress on its outer circumferential surface, due to a strip or wire which has been wound around [it] the ring under stress.

**ATTACHMENT II - Marked up Specification Pages**

FOR THE "SHEET" FOR